

VigoBirch





Description	Birch plywood panel, manufactured in compliance with current regulations	
Use	Automotive, packing, toys	
Classification by face appearance	Superior, Standard, Natural	
Release of formaldehyde	E1, CARB 2 , NAUF	
Gluing class	Class 1, Class 2, Class 3	EN 314-2
Sizes	252 x 125, 135 x 305 cm	
Thicknesses	from 3 to 40 mm	EN 315
Dimensional tolerances	Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m	EN 315
Density	620 kg/m ³ +/- 10%	EN 323
Thermal conductivity	0,12 W/m K	EN 12664
Residual moisture	8 / 12%	EN 322
Reaction to fire	D-s2,d0 - Dfl-s1 (for thicknesses > 9 mm)	EN 13501-1

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.