

VigoHDply





Description	Poplar core plywood covered with high density fibreboard. Manufactured in compliance with all applicable regulations	
Use	A paintable support for furniture	
Release of formaldehyde	E1	
Gluing class	Class 1	EN 314-2
Certifications	PEFC, FSC	
Sizes	244 x 122, 252 x 187, 312 x 212 cm	
Thicknesses	from 12 to 40 mm	EN 315
Dimensional tolerances	Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m	EN 315
Density	560/580 kg/m ³ +/- 15%	EN 323
Thermal conductivity	0,12 W/m K	EN 12664
Residual moisture	8 / 12%	EN 322
Reaction to fire	D-s2,d0 - Dfl-s1 (for thicknesses > 9 mm)	EN 13501-1

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.