

VigoPly Millerighe





Description	Poplar plywood panel with extra strata over and above standard production. Manufactured in compliance with all applicable regulations								
Use	Furniture and post forming, contouring								
Classification by face appearance	Gold, Standard								
Release of formaldehyde	E1, CARB 2 , NAUF								
Gluing class	Class 1, Class 2							EN 314-2	
Certifications	PEFC, FSC, CE2+, CARB 2								
Sizes	244 x 122 cm								
Thicknesses	from 8 to 40 mm							EN 315	
Dimensional tolerances	Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m							EN 315	
Properties	Standard	Unit	Thicknesses - Plies						EN 310
			8/5	10/5	12/7	15/7	18/9	25/11	
Longitudinal flexural strength	UNI EN310	N/mm ²	30	28	27	24	25	29	
Transverse flexural strength	UNI EN310	N/mm ²	28	24	27	28	22	29	
Module of longitudinal flexural elasticity	UNI EN310	N/mm ²	3600	3500	3200	3000	2900	3300	
Module of transverse flexural elasticity	UNI EN310	N/mm ²	3200	3100	3300	3800	3700	3200	
Density	420 kg/m ³ +/- 10%							EN 323	
Thermal conductivity	0,12 W/m K							EN 12664	
Residual moisture	8 / 12%							EN 322	
Reaction to fire	D-s2,d0 - Dfl-s1 (for thicknesses > 9 mm)							EN 13501-1	

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.