

# VigoPly Multiuni





|  |  |            |
|--|--|------------|
| <b>Description</b>                       | Poplar unidirectional plywood, manufactured in compliance with current regulations       |            |
| <b>Use</b>                               | Door frames, furniture   |            |
| <b>Classification by face appearance</b> | Gold, Superior, Standard, Natural  |            |
| <b>Release of formaldehyde</b>           | E1, CARB 2 , NAUF  |            |
| <b>Gluing class</b>                      | Class 1, Class 2   | EN 314-2   |
| <b>Certifications</b>                    | PEFC, FSC, CE2+, CARB 2  |            |
| <b>Sizes</b>                             | 185 x 185 cm   |            |
| <b>Thicknesses</b>                       | from 8 to 40 mm  | EN 315     |
| <b>Dimensional tolerances</b>            | Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m | EN 315     |
| <b>Density</b>                           | 420 kg/m <sup>3</sup> +/- 10%  | EN 323     |
| <b>Thermal conductivity</b>              | 0,12 W/m K   | EN 12664   |
| <b>Residual moisture</b>                 | 8 / 12%  | EN 322     |
| <b>Reaction to fire</b>                  | D-s2,d0 - Dfl-s1 (for thicknesses > 9 mm)  | EN 13501-1 |

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.