

VigoRainbowPly





| | | | | | | | | | |
|---|--|-------------------|----------------------------|-------------|-------------|-------------|-------------|--------------|--------|
| Description | Poplar plywood finished as required in a range of colours, manufactured in compliance with current regulations | | | | | | | | |
| Use | Furniture, shop fitting, partition, general construction | | | | | | | | |
| Release of formaldehyde | E1, CARB 2 , NAUF | | | | | | | | |
| Gluing class | Class 1, Class 2 | | | | | | | EN 314-2 | |
| Certifications | PEFC, FSC, CE2+ | | | | | | | | |
| Sizes | 244 x 122, 252 x 125 cm | | | | | | | | |
| Thicknesses | from 8 to 40 mm | | | | | | | EN 315 | |
| Dimensional tolerances | Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m | | | | | | | EN 315 | |
| Properties | Standard | Unit | Thicknesses - Plies | | | | | | EN 310 |
| | | | 8/5 | 10/5 | 12/7 | 15/7 | 18/9 | 25/11 | |
| Longitudinal flexural strength | UNI EN310 | N/mm ² | 30 | 28 | 27 | 24 | 25 | 29 | |
| Transverse flexural strength | UNI EN310 | N/mm ² | 28 | 24 | 27 | 28 | 22 | 29 | |
| Module of longitudinal flexural elasticity | UNI EN310 | N/mm ² | 3600 | 3500 | 3200 | 3000 | 2900 | 3300 | |
| Module of transverse flexural elasticity | UNI EN310 | N/mm ² | 3200 | 3100 | 3300 | 3800 | 3700 | 3200 | |
| Density | 420 kg/m ³ +/- 10% | | | | | | | EN 323 | |
| Thermal conductivity | 0,12 W/m K | | | | | | | EN 12664 | |
| Residual moisture | 8 / 12% | | | | | | | EN 322 | |
| Reaction to fire | D-s2,d0 - Dfl-s1 (for thicknesses > 9 mm) | | | | | | | EN 13501-1 | |

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.