

VigoPlyVC





|   |   |                   |                            |             |             |             |             |             |        |
|---|---|-------------------|----------------------------|-------------|-------------|-------------|-------------|-------------|--------|
| <b>Description</b>                                | Plywood panel coated with PVC. Manufactured in compliance with all applicable regulations |                   |                            |             |             |             |             |             |        |
| <b>Use</b>  | Caravans, campers, automotive industries  |                   |                            |             |             |             |             |             |        |
| <b>Release of formaldehyde</b>                    | E1, CARB 2 , NAUF   |                   |                            |             |             |             |             |             |        |
| <b>Gluing class</b>                               | Class 1, Class 2  | EN 314-2          |                            |             |             |             |             |             |        |
| <b>Certifications</b>                             | PEFC, FSC   |                   |                            |             |             |             |             |             |        |
| <b>Sizes</b>                                      | 244 x 122 cm  |                   |                            |             |             |             |             |             |        |
| <b>Thicknesses</b>                                | from 3 to 40 mm   | EN 315            |                            |             |             |             |             |             |        |
| <b>Dimensional tolerances</b>                     | Length and width: +/-3,5 mm. Thickness +(0,2+0,03t); -(0,4+0,03t). Orthogonality: 1 mm/m  | EN 315            |                            |             |             |             |             |             |        |
| <b>Properties</b>                                 | <b>Standard</b>   | <b>Unit</b>       | <b>Thicknesses - Plies</b> |             |             |             |             |             | EN 310 |
|   |   |                   | <b>8/5</b>                 | <b>10/5</b> | <b>12/7</b> | <b>15/7</b> | <b>18/9</b> | <b>20/9</b> |        |
| <b>Longitudinal flexural strength</b>             | UNI EN310   | N/mm <sup>2</sup> | 36                         | 28          | 30          | 29          | 30          | 29          |        |
| <b>Transverse flexural strength</b>               | UNI EN310   | N/mm <sup>2</sup> | 32                         | 24          | 32          | 37          | 27          | 39          |        |
| <b>Module of longitudinal flexural elasticity</b> | UNI EN310   | N/mm <sup>2</sup> | 3525                       | 3600        | 3130        | 3270        | 3480        | 3150        |        |
| <b>Module of transverse flexural elasticity</b>   | UNI EN310   | N/mm <sup>2</sup> | 3150                       | 3300        | 3290        | 3900        | 3790        | 3580        |        |
| <b>Density</b>                                    | 420 kg/m <sup>3</sup> +/- 10%   |                   |                            |             |             |             |             |             | EN 323 |
| <b>Residual moisture</b>                          | 8 / 12%   |                   |                            |             |             |             |             |             | EN 322 |

The data in this sheet show approximate values obtained from internal testing on normal production. It is the buyer's responsibility to determine whether the products of E.Vigolungo SpA are suitable for the applications for which they are intended to be used and that the modes of transport and use comply with current regulations.